


COOLANT ANALYSIS



Coolant Analysis

Monitoring an engine's cooling system performance is imperative, as research shows that 40% to 60% of all diesel engine failures are caused by a faulty cooling system. Therefore, a key factor in avoiding dreaded premature engine failure is to keep the cooling system operating optimally by using the most appropriate coolant and regularly measuring its chemical and physical properties.

Without proper maintenance, cooling systems can lead to failure modes such as overheating, overcooling, pitting, cavitation erosion, cracked heads, piston seizures, reduced critical clearances, low oil viscosity, increased wear and plugged radiators.

The effects of these problems manifest as:

- Acid/alkalinity balance (corrosion)
- Scale and deposit formation (blockages)
- Electrolytic corrosion (electrolysis)
- Cavitation erosion (liner pitting)
- Galvanic corrosion
- Additive loss
- Aeration (erosion)
- Rust

The longer a particular coolant remains in an engine, the greater the probability of these problems occurring. With increased coolant service life, therefore, the need for regular coolant monitoring increases.

WearCheck has devised a set of tests to determine whether the coolant is in good condition and capable of doing its job. If any of the pre-determined parameters are found to be out of spec then remedial action can be taken to ensure the healthy, normal operation of the cooling system and, in turn, the engine.

Coolant Tests:

- Glycol % (Test Method: ASTM D3306)
- pH (Test Method: ASTM D1287)
- Nitrate ppm (Test Method: in-house)
- Molybdate ppm (Test Method: in-house)
- TDS Total Dissolved Solids ppm (Test Method: OEM)
- Foam (Test Method: in-house)

Other tests include:

- Freeze Point
- Boil Point



Contact Details

South African Offices & Laboratories

Head Office

Unit 4, The Terrace, Westway Office Park,
Westville, KwaZulu-Natal
t : +27 31 700 5460
e : support@wearcheck.co.za

Bloemfontein

Unit B, 4 Milner Road
Waverley
t : +27 51 101 0930
e : support@wearcheck.co.za

Eastern Cape

8 Van Wyk Road,
Westering
t : +27 82 290 6684
e : support@wearcheck.co.za

Gauteng

30 Electron Avenue,
Isando
t : +27 11 392 6322
e : support@wearcheck.co.za

Middelburg & Witbank

Unit 7a Nungu Industrial Park
13 Mandela Drive, Middelburg
t : +27 13 246 2966
e : support@wearcheck.co.za

Northern Cape

20 Kelkiewyn Street,
Kathu, 8446
t : +27 66 474 8628
e : support@wearcheck.co.za

Rustenburg

221A Beyers Naude Street,
Rustenburg, 0299
t : +27 83 938 1410
e : support@wearcheck.co.za

Western Cape

Unit 17, Prosperity Park, 10 Computer Rd,
Montague Gardens, 7441
t : +27 21 001 2100
e : support@wearcheck.co.za

International Offices & Laboratories:

DRC

Kibali Mine
Kibali
t : +260 977 622 287
e : boniface@wearcheck.co.zm

Ghana

Adjacent PanAfrican (Zen Yard),
Akyempin Road, Tarkwa
t : +233 54 431 6512
e : supportgh@wearcheck.com.gh

India

#16-B Kamokoti Nagar Main Road, Palli Karanai,
Chennai, 600 100, Tamilnadu
t : +91 44 4557 5039
e : nissar@wearcheck.co.in

Mozambique

Esquina da EN4 and Mozal Road, Talhão no. 11/15,
Bairro Mussumbuluco, Municipio da Matola
t : + 258 85 792 7933
e : supportmz@wearcheck.co.mz

Namibia

Unit 14, Lafrenz Industrial Park – Erf R/E 26 W,
Rendsburger Street, Windhoek
t : +264 81 141 7205
e : supportna@wearcheck.co.na

UAE – Dubai

Plot 271, Sector 18
AlJarf Area, Ajman
t : +971 6 740 1700
e : operations@wearcheckpm.com

Zambia

Plot 3717, Prescott Road
Light Industrial Area, Kitwe
t : +260 212 210 161
e : supportzm@wearcheck.co.zm

Zimbabwe

23 Amby Drive, Amby,
Harare
t : +263 24 244 6369
e : supportzw@wearcheck.co.zw